



**Technical Data Sheet** 

**Screen Printing inks** 

2022 24,Jan

## Ink

## **PET Series**

## FIELD OF APPLICATION

## **Substrates**

The screen-printing ink PET is excellently suited to print onto

PC

**PET** 

**PVC** 

## Field of Use

PET series is designed to print on PET, PVC, PC material to make labels, thin Membranes.

The ink is used as 1 component ink.

## **CHARACTERISTICS**

This soft matt gloss with excellent sieving and leveling properties, physically drying screen-printing ink exhibits good mechanical & chemical resistance as well as good flexibility and adhesion. Excellent printability and stable in color matching. Low odour, good reprinting, and post processing abilities.

## **HOW TO USE**

Dilute the ink with 10%-20% TP-65 (slow dry thinner) or TP-69 (medium dry thinner). Use TP-67 to make the drying slower. PET series is designed to dry slowly in order to avoid clogging and have good reprint capabilities.

For overprinting, the next color is printed only after tacking free.

Mesh Recommended-77T-120T

Tack Free Time	5-10 minutes	Natural Cure
Hard Drying Time	12-24 hours	Natural Cure
Force Drying	20-30	
Time	minutes	70°C-90°C

If several layers are printed longer drying time is recommended

## **CLEANER**

Use TP-65 for cleaning the screen /washing up.

#### RANGE OF COLORS

## **Basic Colors**

104-White

203-Original Yellow

209-Mid Yellow

302-Deep Red

305-Orange

3038-Light Resistant Pink

401-Violet

403-Original Blue

404-Ultramarine Blue

408-Cyanine Blue

501-Black

601-Green

## **Transparent Colors**

Yellow

Red

Blue

Green



# Farbatone®

## **Technical Data Sheet**

## **Screen Printing inks**

2022 24,Jan

#### **Fluorescent Colors**

131-Fluorescent Yellow 133-Fluorescent Red

140-Fluorescent Green

159-Fluorescent Pink

## **Metallic Colors**

801 Silver 901 Pale Gold

## **4 Color Process Printing inks**

Process Black Process Red Process Yellow Process Blue

## **ADDITIVES**

## Thinner:

Before production, the viscosity of the screen-printing ink has to be adjusted by the addition of thinner.

Thinner TP-69, fast drying (addition 15%-25%)

Thinner TP-65, standard drying (addition 15%-25%)

## Retarder:

Thinner TP-67, very slow drying (addition 15%-20%)

Retarder TP-67 can be used along with TP-65 or TP-61 to meet the printing requirement.

## **Custom Colors**

Pantone/RAL/TPX colors are custom made colors and can be developed as per request.

#### **TYPE OF PACKING**

1-kg Can

#### **SHELF LIFE**

The shelf life for an unopened ink container if stored in dark room at a temperature of 15°-25° C is

- 1) 2 years for the basic colors
- 2) 1 year for Transparent, Metallics and fluorescent colors.

Under different conditions, particularly higher storage temperatures, the shelf life is reduced. In such case, the warranty given by Spinks expires.

#### **PRECAUTION**

- Before use, check if the ink is properly selected, open the packing to check if the ink is under good condition, including no gelling, no color change etc. and stir well before use
- 2) Please perform a printing test before formal printing, After 24 hours of natural volatilization or drying at high temperature, check its adhesion and properties meet the requirement or not.
- 3) No other additive is added during use.
- 4) Please refer MSDS before use.
- 5) Be sure to do trials before commercial run to confirm that the product fits the purpose



# Farbatone<sup>®</sup>

**Technical Data Sheet** 

**Screen Printing inks** 

2022 24,Jan

- 6) Additional technical information may be obtained from our Technical Department.
- 7) All characteristics described in this Technical refer Data Sheet exclusively to the standard products listed under range, provided that they are processed in accordance with the intended use and only when used with the recommended additives. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, they shall be limited to the value of the goods delivered by us and utilized by you with respect to any and all damages not caused intentionally or by gross negligence.